

RHEO-OPTICS OF LIVING POLYMERS: SMALL-ANGLE LIGHT SCATTERING PATTERNS OF CETYLTRIMETHYLAMMONIUM TOSYLATE SOLUTIONS IN PRESENCE OF SODIUM BROMIDE

Moisés Romero-Ureña¹, Luis Medina-Torres², Octavio Manero Manero³, J. Esteban López-Aguilar¹

¹Universidad Nacional Autónoma de México, Departamento de Ingeniería Química, Facultad de Química, Mexico. ²

Univeridad Nacional Autónoma de México, Facultad de Química, Mexico. ³Univeridad Nacional Autónoma de México, Instituto de Investigaciones en Materiales, Mexico.

In this work, we present a study based on Small-Angle Light Scattering (SALS) patterns of the simple shear-flow response of semi-diluted solutions of cetyltrimethylammonium tosylate (CTAT; 5.5 wt.% - 0.12 M), in the presence of sodium bromide (NaBr) at different concentrations $[\text{NaBr}] = \{0, 0.12, 0.19, 0.25, 0.3\}$ M [1]. We provide evidence of a relationship between rheological and light scattering data that reveals a transition into a fast-breaking regime in the dynamics of wormlike micelles formed by CTAT/NaBr system. This transition is evident with the increasing NaBr concentration, which is marked by the following features: (i) a decrease in the relaxation time λ_0 , accompanied by (ii) a dimmish of the viscosity magnitude at low shear rates, η_0 . (iii) Formation of butterfly-like scattering patterns, caused by concentration fluctuations due to the imposed flow, correlated with (iv) the development of banded flow in the velocity gradient direction, and (v) signs of a transition to a distinct flow regime, recorded through the formation of a second peak in the structure factor. In addition, we report that the Cox-Merz rule is fulfilled at molar salt-to-surfactant ratios of $R \geq 1.5$ which, according to estimates of the BMP model, results in shorter structure-recovery time-scales than the characteristic-time of the flow. Finally, from a theoretical perspective, we provide predictions for the shear-stress and the first normal-stress growth coefficients in transient start-up simple shear flow using the BMP model for the samples with $R=0$ and $R=1.5$, where it is observed that the $R=1.5$ solution displays overshoot responses at shear rates corresponding to the non-monotonic region of the steady-state flow curve. Our results are in-line with experimental findings in other investigations [2-6].

Keywords: Living polymers, Fast-breaking regime, Light scattering patterns

Acknowledgment:

The support from Consejo Nacional de Humanidades, Ciencias y Tecnologías (CONAHCYT, México) for the scholarship (CVU number 1084375) to fund his post-graduate studies and the project CONAHCYT; grant number CF-2023-I-318.

The support from Universidad Nacional Autónoma de México (PAPIIT IA102022, IN106424, IN100623 and PAIP 5000-9172 Facultad de Química).

Presenting author's email: boch@comunidad.unam.mx